


Gaine Carbone 45° Diam 20mm 27g/ml

Caracteristiques / Characteristics		Nominal
Poids total / Mass per unit area	g/m ²	432
	g/ml	27
Compatibilité/ Compatibility		Epoxy

Construction	Nature De La Fibre / Fiber Description	Distribution Du Poids / Weight Distribution
45°	FT300 6000 50A S15	432 g/m ² ou 27gr/m

Conditionnement / Packaging		Nominal
Diamètre standard / Standard diameter	mm	20
Longueur approx/ Approx length	ml	100



LEGAL NOTES: SICOMIN reserves the right to change the properties of its products. All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data and tolerance may vary due to circumstances beyond our control. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

MENTIONS LÉGALES : SICOMIN se réserve le droit de modifier les propriétés du produit. Toutes les caractéristiques spécifiées dans cette Fiche technique sont basées sur des tests de laboratoire. Les mesures et leurs tolérances effectives peuvent varier pour différentes raisons. SICOMIN se réserve le droit Aucune garantie de quelque nature que ce soit, sauf que les matériaux fournis sont de qualité standard. Tous les risques et responsabilités découlant de la manutention, le stockage et l'utilisation des produits, ainsi que le respect des restrictions légales applicables, incombe à l'utilisateur.